Pyra™





Application:
Jpholstery fabric
Composition:
100% Polypropylene
Width:
143cm Tolerance ± 2%
Weight:
225gms/m2 Tolerance ± 5%
Abrasion:
Tested in accordance with BS EN ISO 12947-1:1999 as modified by Annex F of BS 2543: 2006 to 60,000 rubs Martindale.
Meets the requirements of BS 2543: 2004
Flame Retardancy:
BS 7176: 2007 Direct Test for Low Hazard premises.
BS EN 1021 – 1&2: 2006 (passes cigarette and match)
Note: Flammability performance is dependent on foam used.
Light Fastness:
5+ (ISO 105 – B02:1999)
Colour Matching:

Batch to batch variations in shade may occur within commercial tolerances. We recommend that fabric be examined before use as no claims

will be considered after cutting.

Product Development:
We reserve the right to change the specification of our products in line with our product development programme without notice.
Fabric Care And Maintenance:
Clean using a proprietary upholstery shampoo. Please refer to our fabric care guide.
Availability:
All our fabrics are generally available ex-stock for immediate despatch.
Technical Assistance:
Our technical staff will be pleased to offer advice on F.R. and other matters.
Guarantee:
Fabric guaranteed for 5 years under normal wear and tear. See our Terms and Conditions